

PRODUCT DESCRIPTION

Mercasol 633



Issue: 2009-06-10 SH

APPLICATION AREAS

Mercasol 630 is a lubricating corrosion protection grease, meant to be used for industrial applications. Examples of applications are steel sheet joints, joints beneath protection trims, wires and machinery parts on ships and off-shore platforms.

CHARACTERISTICS

Mercasol 633, which has very good corrosion protection, is a solvent free, water resistant, beige lubricating grease. When wanted, extra thick layers can be applied without any sagging, which give a very good corrosion protection and lubrication over a long period of time.

PRE-TREATMENT

Surfaces which are meant to be treated shall be dry and free of rust, dirt, salt, oil and similar.

APPLICATION

Application should be performed at temperatures between +10 and +40°C.
Mercasol 633 is applied by brush or pressure gun.

RECOMMENDED FILM THICKNESS

100-200µm wet layer.

MATERIAL CONSUMPTION

Approximately 0,10-0,20 liter/m².

CLEANING

Equipment is cleaned with aliphatic naphtha. Staining and overspray is favourable being removed by aliphatic naphtha..

DRYING TIMES

N.a.

PACKAGING

10 litres can

SAFETY, HANDLING AND STORING

See material safety data sheet (MSDS) for the product at www.auson.se

When stored according to given instructions, the storing time is 12 months.



Visiting address:: Verkstadsgatan 3
Postal address: 434 42 KUNGSBACKA
Telephone: +46 (0)300 56 20 00
Telefax: +46 (0)300 56 20 01
www.auson.se



PRODUCT DESCRIPTION

Mercasol 633



Issue: 2009-06-10 SH

TECHNICAL DATA

<u>Property</u>	<u>Statement</u>	<u>Method</u>
Colour	beige	-
Film	Grease	-
Flash point	n.a.	ISO 2719
Dry content by weight	> 97%	ISO 3251
Dry content by volume	> 97%	-
Viscosity	~ 8500 mPas	Rheolab Physica MC10
Density	~ 1,22 g/cm ³	SS 18 41 11 / ISO 2811

The above mentioned technical information indicates the guideline values. It does not indicate the exact values nor the upper/lower limits for variations. The purpose of this information is to provide a general description of the product's technical quality. The information does not constitute any kind of guarantee as regards the product's specific characteristics or the suitability of the product for a certain field of application.



Visiting address: Verkstadsgatan 3
Postal address: 434 42 KUNGSBACKA
Telephone: +46 (0)300 56 20 00
Telefax: +46 (0)300 56 20 01
www.auson.se

